

Technical Data Sheet

PIRMAC™ 48 Rigid Polyisocyanurate Insulation

PIRMAC™ 48 Polyisocyanurate (PIR) Complies with ASTM C591, Grade 2, Type III

Properties	Test Method	Value
Temperature	Upper Lower	+149°C -183°C
Density	ASTM D1622	40 Kg/m ³
Compressive Strength Parallel Compressive Strength Perpendicular	ASTM D1621 ASTM D1621	330 Kpa 230 Kpa
Tensile Strength Parallel Tensile Strength Parallel Perpendicular	ASTM D1623 ASTM D1623	450 Kpa 340 Kpa
Closed cell content	ASTM D2856	92%
Thermal Conductivity (at -10°C) Thermal Conductivity (at -20°C)	ASTM C518	0.024 W/m.k 0.025 W/m.k
Fire Properties Flame Spread	DIN 4102 ASTM E84	B2 <25
Water Absorption Water Vapor Permeability	ASTM C272 ASTM E96	0.8 (Max. Vol%) 4.4 max, (ng/Pa-s-m)

Egypt:

Misalla Industrial Service.
Address: Smouha Green Towers, Building #4, Alexandria.
Tel.: (203) 5899040
Fax : (203) 5899041
E-Mail: info@misalla.com
Website: www.misalla.com

Kingdom of Saudi Arabia:

Energy Construction.
Address: Sabian Street, Behind Arab National Bank, Jeddah, P.O. Box 50595
Tel.: +966 2 674 3892 Ext. (114)
Fax : +966 2 674 3823
E-Mail: w.fahmy@energygcc.com
Website: www.misalla.co



Our Chemical Systems Provided By:



PIRMAC™ Rigid Polyisocyanurate Insulation