


# CRAD-X<sup>TM</sup>

INSULATED PIPE SUPPORTS

120

CRAD-X<sup>TM</sup>



**Misalla Industry & Chemicals**

**CONTACT**

Tel. (+203)4263588  
(+20)1154452494  
Fax. (+203)4263589

Mail: [info@misalla.com](mailto:info@misalla.com)  
Website: [www.misalla.com](http://www.misalla.com)

**Office Address:** St. 20, Smouha  
Green Towers, Tower no. 4, Smouha,  
Alexandria - Egypt.

**Factory Address:** Petrochemical Rd.  
Merghem Amria - Alexandria - Egypt



# CRAD-X<sup>TM</sup>

# 120 HIGH DENSITY POLYURETHANE FOAM PIPE SUPPORTS

PROPERTIES	TEST METHOD	VALUE
Density	ASTM D1622	120 Kg/m <sup>3</sup>
Compressive Strength (At 20°C)	ASTM D1621	1.14 Mpa
Compressive Strength (At -160°C)	ASTM D1621	1.04 Mpa
Tensile Strength (At 20°C)	ASTM D1623	0.97 Mpa
Tensile Strength (At -160°C)	ASTM D1623	1.57 Mpa
Closed Cell Content	ASTM D2856	95%
Thermal Conductivity @ 20°C	ASTM C518	0.031 W/m.k
Thermal Conductivity @ -160°C		0.029 W/m.k
Leachable Halides	ASTM D871	Less than 20 Ppm
Water Absorption	ASTM C272	1.28 (Max. Vol%)



Revision: 03

Issued: 2021



TEL. (+203) 4263588  
(+20) 1154452494  
FAX. (+203) 4263589

OFFICE ADDRESS St. 20, Smouha Green Towers, Tower no. 4 ,  
Smouha, Alexandria - Egypt.  
FACTORY ADDRESS Petrochemical Rd. Merghem Amria -  
Alexandria - Egypt

MAIL [info@misalla.com](mailto:info@misalla.com)  
WEBSITE [www.misalla.com](http://www.misalla.com)